

# Technical Data Sheet

## AS-206

### Bathroom & Sanitary Sealant

#### Physical Properties

**Base:**

Silicone polymer

**Appearance:**

Non-sagging paste  
(Before curing)

Elastic rubber  
(After cured)

**Colours:**

Translucent & white

**Tack-free time:**

10 – 30 minutes  
(at 25 °C & 50% R.H)

**Application temperature:**

-20 °C to 50 °C

**Service temperature:**

Up to 150 °C

**Storage:**

Store in a dry and cool place  
with temperature below 30 °C.

**Shelf life:**

12 months

**Packaging:**

Content	Quantity/ carton
300 mL cartridge	24



#### Description

ALSEAL Bathroom & Sanitary Sealant is a one component, mildew-resistant, 100% neutral-cure silicone sealant formulated for applications in areas with high humidity and temperature. The fungal resistance property of this sealant has been tested against ASTM G21-02 and found to have a strong fungistatic effect. It will cure to form a durable, flexible, waterproof seal on most common wet area building materials. It is tested to have a low VOC content, in compliance to the SCAQMD Rule 1168 (Adhesive and Sealant Applications).

#### Features

- ◆ Neutral curing system
- ◆ Anti-fungus
- ◆ Mildew resistant (Anti-fungus)
- ◆ Low VOC compliant
- ◆ Permanently flexible
- ◆ Indoor and outdoor use

#### Applications

- ◆ Good adhesion on most ceramics, glass and plastics. Widely used for grouting ceramic tiles, bedding tile accessories and sealing shower heads, tubs, rimless, sinks, kitchen and bathroom fixtures.

#### Technical Data

Curing system	: Moisture curing, neutral
Specific gravity	: 0.98 - 1.02 g/mL
Slump (ASTM D2202)	: <1 mm
Maximum tensile strength (ASTM D412)	: 1.3 N/mm <sup>2</sup>
Elongation at break (ASTM D412)	: 390 %
Shore A hardness (ASTM C661)	: 23
Anti-fungal testing (ASTM G21)	: 0 rating (No growth)
VOC content (USEPA Method 24)	: 57.38 g/L

#### Approvals/ Specifications

AS-206 meets the requirements of the following specifications:

- ◆ ASTM G21 (Anti-fungus)
- ◆ Low VOC - USEPA Method 24 under SCAQMD Rule 1168

#### Usage Instructions

1. Surfaces must be clean, dry and free of dirt, grease, oil or water.
2. Surfaces should be cleaned with alcohol, M.E.K. or other suitable solvent. Do not use soap or detergent.
3. For a neat finish, apply masking tape and remove it before sealant skins over.
4. Cut nozzle at 45° angle to desired bead-width and apply to substrate with cartridge gun.
5. Tool the sealant within 10 minutes of extrusion before it skins. Tack-free in 20 minutes.
6. Uncured sealant can be cleaned up with mineral spirits.

#### Clean Up

- ◆ Wet sealants can be cleaned up with acetone or mineral spirits.
- ◆ Cured sealants can only be removed mechanically.



## AS-206 Bathroom & Sanitary Sealant

### Joint Design

- ◆ The specified sealant bead size should be calculated to comply with the compression and extension capabilities of the sealant in relation to the anticipated joint width due to expansion and contraction.
- ◆ Generally calculation of the width sealant bead should be computed on the basis of a maximum  $\pm 20\%$  movement capability
- ◆ Minimum joint depth should not be less than 6 mm to accommodate movement.
- ◆ Sealant design joint width-to-depth ratio should be 2:1.

### Coverage

Width	Depth	Coverage (300 ml) *
6 mm	6 mm	7.58 meter
10 mm	10 mm	2.73 meter
20 mm	10 mm	1.36 meter
25 mm	12 mm	0.91 meter

\* The coverage figures shown above are approximate linear meter run based on 10% wastage assumption. Actual coverage may vary.

◆ Calculation formula:

$$X / [(Y \times Z) \times 1.1] = \text{Coverage}$$

X = volume of cartridge (or sausage) in ml,

Y = joint width in cm, Z = joint depth in cm,

1.1 = 10% wastage assumption,

Coverage = linear meter run in cm per cartridge

### Limitation

Not recommended for following applications:

- ◆ Below waterline or permanent water immersion.
- ◆ Traffic areas subject to abrasion.
- ◆ Polycarbonate and polyacrylate, if under tension.
- ◆ Applications that requires the sealant to be painted.
- ◆ Neoprene rubber

### Caution

Product releases methylethylketoxime during application and curing. May cause an allergic skin reaction. Causes serious eye irritation. Wear protective gloves and eye protection. IF ON SKIN: Wash with soap and water. IF IN EYES: Rinse continuously with water for several minutes. Remove contact lenses if present and easy to do – continue rinsing. If skin irritation or a rash occurs: Get medical advice/attention. If eye irritation persists: Get medical advice/attention. Wash contaminated clothing before reuse. Keep out of reach of children. Contains aminosilane. May produce an allergic reaction. Safety data sheet available on request. For further health and safety information, consult the latest safety data sheet.

### Disclaimer

Every endeavour has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. The company cannot accept any responsibility for the loss or damage that may result from the use of the information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm suitability of this product by their own tests.